

CONVERTEX

TESSUTI ELASTICI MADE IN ITALY

CONVERTEX SRL - Sede Legale: Via Volturmo 2/C, 00185 Roma - Sede Operativa: Via Colalillo, 86021 Bojano CB - P. Iva 02017750429
tel 0874.778050, 380.7591909 - fax 0874 782327 - numero verde 840 690309 - info@convertex.it - ww.convertex.it - cap. soc. € 200.000

FABRIC: SOGNO

Specifiche tecniche – Technical data sheet November 2023

Nome tessuto/Fabric name: **SOGNO - laminated net with a full plastics coverage 100% polyester**

NC 5903 9099

TARIC RU 5903 9099 00

Tipo tessuto/Fabric type: **Power net laminated**

Finezza/Machine gauge: **56**

Composizione/Composition: **82% polyamide – 18% elasthane**

Altezza/Width: **150 cm, minima utile / usable width: 140 cm**

Peso/Weight: **50 g/m² ±10% (i.e. weight tolerance: 45 – 55 g/m²)**

Elasticità/Zwick stretch (15 N) **Ordito / Warp: 195% (155 – 240 %)**

Trama / Weft: 55% (46 – 65 %)

Restringimento/Shrinkage (DIN 53897):

Ordito / Warp: 8%

Trama / Weft: 8%

Solidità colori/Colour Fastness: **3-4**

DIN 54014 ISO 105 C01 - DIN 54006 ISO 105 E01

DIN 54020 ISO 105 E04 - DIN 54021 ISO 105 X12

Accordingly to Oko-Tex Standard 100



ИНСТРУКЦИИ ПО ТЕХНИЧЕСКОМУ ОБСЛУЖИВАНИЮ

Ручная стирка в холодной воде или при температуре 30° C с использованием нейтрального моющего средства

Не подвергать химической чистке

Избегайте чрезмерного сухого и влажного трения. Избегайте длительного замачивания, поскольку фольга изготовлена на водной основе.

Гладить с изнаночной стороны с проложенной тканью без пара (утюг - 1 балл)

Потери отделочного/декоративного материала являются нормальным явлением.

При первой стирке все покрытия могут потерять блеск, затем он стабилизируется.

Обратите внимание, что плотность прилегания фольги зависит от условий использования и назначения ткани.

Одним из факторов, влияющих на герметичность, является тип условий хранения и консервации, которым подвергается ткань (влажность, тепло и т.д.).

CARE INSTRUCTIONS

Cold water or 30° C Hand washing with neutral soap.

Do not dry clean.

Avoid excessive dry and wet rubbing. Avoid prolonged soaking since the foils are water based.

Iran on the reverse side with cloth in between without steam (Iron 1 point).

Eventual loss of finishing/decorating material is normal.

All foils may loose brightness during the first washing to become more stable after.

We recommend that the strenght of the foil depends on use and destinations of the fabric.

One factor that affects the strenght is the type of storage conditions that has undergone the fabric (humidity, heat, etc)